

CHM Composites Ltd | Office 5 | Business Development Centre | Turners Hill Road  
 Business Park | Craven Arms SY7 8DZ | UK  
 T: + 44 (0) 797 7319753  
 E: info@chmcomposites.com | W: [www.chmcomposites.com](http://www.chmcomposites.com)  
 Registered company 5703965



## Technical Data Sheet

**Manufacturer:** YF International BV, Netherlands

**Product:** AF 20/1 G    AF 25-G    AF 10

**Description:** Para-aramid short fibres (pulped: dry processed fibrillated)

**Applications:** Used as asbestos replacement gasket materials and friction linings

**Properties:**

	<b>AF 20/1 G</b>	<b>AF 25-G</b>	<b>AF 10</b>
<b>Structure</b>	pulp	pulp	pulp
<b>Colour</b>	yellow	yellow	yellow
<b>Composition</b>	para-aramid ≥ 98% fibre finish < 2% humidity 2-5%	para-aramid ≥ 98% fibre finish < 2% humidity 2-5%	para-aramid ≥ 98% fibre finish < 2% humidity 2-5%
<b>Fibre length range</b>	0 - 2.5mm	0 - 3.0mm	0 - 10mm
<b>Average fibre length</b>	1.0 - 1.2mm	1.2 ± 0.1mm	6 ± 1mm

**Packaging:** Polyethylene bags

**AF 20/1 G**    5kg – 30 bags per pallet  
 or 20kg – 16 bags per pallet

**AF 25-G**    20kg – 16 bags per pallet

**AF 10**    20kg – 16 bags per pallet

**Health and Safety:** Manufacturers MSDS available on request

The data contained herein are nominal and are not intended to be a guaranteed specification  
 The user must be satisfied that the product is entirely suitable for the purpose